

## ARBOSIL 1096 S

Arbosil 1096 S is a one part Low Modulus Neutral Cure Silicone Sealant which cures on exposure to moisture vapour to form an elastic silicone rubber.

### MAIN APPLICATIONS

Recommended for use in many forms of construction including glass to glass joints, curtain wall assemblies, perimeter seals on curtain walling, perimeter sealing of polyester powder coated and PVCu frames and glazing of windows in swimming pool buildings. Approved by Pilkingtons and other major glass manufacturers for use with laminated glass. Suitable for use as a weather seal with structural glazed assemblies.

**NB:** It is not recommended for overpainting, and use against natural stone.

### APPLICATION INSTRUCTIONS

#### Joint Preparation

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate Arbo Cleaner. Primers may be required on some substrates. It is recommended that Adsheed Ratcliffe Technical Services Department should be consulted and advice obtained with regard to the choice of primer for specific purposes.



#### Joint Backing

Where applicable, appropriate joint filler e.g. closed cell polyethylene foam, should be used to provide the correct joint depth. All joint preparation, priming, and sealant application should be carried out in accordance with BS 8000 Part 16, the British Standard for the sealing of joints in buildings using sealants.

#### Application

Arbosil 1096 S is supplied in polyethylene 380ml cartridges and can be applied into the joint using an Arbo Caulking Gun

**TECHNICAL DATA**

Colours	White, Black, Grey, Translucent, Anthracite, Mahogany, RAL7016
Skin Time at 20° C/65 % RH:	10 minutes
Application Temperature:	+ 5° C to + 50° C
Service Temperature:	- 50° C to + 150° C
Typical Shore Hardness:	30
Cure Rate at 20o C/65 % RH:	2mm/24 hours
Chemical Resistance:	Resistant to most dilute acids and alkalis. Organic solvents may cause the sealant to swell and lose adhesion
UV Resistance:	Very Good
Service Life:	25 years +
Movement Accommodation:	Butt joints (movement in tension and compression): 50 %.
Lap joints (movement in shear):	100 %.

**JOINT SIZE SUITABILITY****Joint width**

Minimum 6mm

Maximum 25mm (single application);

50mm (multiple applications)

**Joint Depth**

Minimum 10mm on porous substrates

Minimum 6mm on non-porous substrates

Maximum 15mm

**Width: Depth ratio** (within above min/max restrictions)

2:1 butt joints

1:1 lap joints

**HEALTH AND SAFETY**

Contains Oximosilanes. Please consult Safety Data Sheet for full information.

**PACKAGING**

25 x 380ml Polyethylene Cartridges per box.

Polyethylene Nozzles are included in each box.

## ACCESSORIES

### Primers

Arbo Primer 2650 (500ml tin) Yield approximately 125 metres per tin  
 Arbo Primer 2402 (500ml tin) Yield approximately 200 metres per tin  
 Arbo Primer 2172 (500ml tin) Yield approximately 200 metres per tin

### Cleaners

Arbo Cleaner No.17- 1 Litre Tin  
 (Xylene based – not suitable for use with plastics or delicate finishes)  
 Arbo Cleaner No. 16 - 1 Litre Tin  
 (Alcohol Based)

### Ancillary Equipment

Polyethylene Nozzles  
 Arbo Caulking Guns

## QUANTITY ESTIMATOR

Joint Size (mm)	Metres/Litre
6 x 6	27.8
9 x 6	18.5
12 x 9	9.3
18 x 10	5.6
25 x 10	4.0

## SPECIFICATION COMPLIANCE

BS EN ISO 11600 – F/G – 25 LM
BS 5889 Type A: 1989

**IMPORTANT:** The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.



CARLISLE® Adshead Ratcliffe & Co. Ltd United Kingdom

Derby Road | Belper  
 Derbyshire

DE56 1WJ  
 United Kingdom

T +44 (0)1773 826661  
 F +44 (0)1773 821215

E info.arbo@ccm-europe.com  
[www.arbo.co.uk](http://www.arbo.co.uk)