



Technical Data Sheet

DOWSIL™ 786 Silicone Sealant

FEATURES & BENEFITS

- Cured sealant is mildew resistant
- Remains permanently flexible without shrinking, cracking, crumbling or drying out
- Resists staining, spotting and color changes
- Retains original design properties even after years of exposure
- Complies with FDA Regulation No. 21 CFR 177.2600

COMPOSITION

- One-part, acetoxy-cure silicone rubber sealant
- Contains an antimicrobial

Silicone rubber sealant for surfaces, showers, tubs, sinks and plumbing fixtures which contains an antimicrobial. Product has been tested against a spectrum of microbes.

APPLICATIONS

DOWSIL™ 786 Silicone Sealant is designed to seal nonporous surfaces around showers, tubs, sinks and plumbing fixtures where conditions of high humidity and temperature extremes exist. Typical applications include:

- Sealing around shower-tub enclosures, tubs, sinks, urinals and whirlpools
- Sealing around bathroom fixtures
- Waterproofing rimless sinks
- Ceramic tile grouting

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Property	Unit	Result
As Supplied			
ASTM C 679	Tack-Free Time at 25°C (77°F), 50% RH	minutes	20
	Tooling Time	minutes	5 – 11
ASTM C 639	Flow, sag or slump		Nil
ASTM C 639	Color		White, translucent white, almond, clear, gray
ASTM C 603	Extrusion Rate	g/min	350
ASTM C 639	Volatile Organic Content (VOC) ²	g/L	22
As Cured – 7 days at 25°C (77°F) and 50% RH			
ASTM D 2240	Durometer Hardness, Shore A	points	25
ASTM D 412	Ultimate Tensile Strength	psi (MPa)	325 (2.1)
ASTM D 624	Tear Strength	ppi (kN/m)	25 (4.4)
ASTM C 794	Peel Strength	pli (kN/m)	20 (3.5)

¹ASTM: American Society for Testing and Materials.

²Based on South Coast Air Quality Management District of California. Maximum VOC is listed both inclusive and exclusive of water and exempt compounds.

DESCRIPTION

DOWSIL 786 Silicone Sealant is a single-component, ready-to-use silicone rubber sealant. The sealant adheres to many surfaces, such as porcelain, cultured marble, painted areas and glass, without the use of a primer.

Cured DOWSIL 786 Silicone Sealant is mildew resistant.

DOWSIL 786 Silicone Sealant is available in white, translucent white, almond, clear and gray.

DOWSIL 786 Silicone Sealant is compatible with most substrates. However, adhesion and compatibility should be evaluated in each instance prior to use.

Primers: Primers are not usually required on ceramic, glass and glazed surfaces. It is possible that certain products should be primed for maximum adhesion. A recommended primer for use with metals, Formica® and plastics is DOWSIL™ 1200 OS Primer. Refer to the Construction Americas Technical Manual, No. 62-1112, for more specific recommendations. In cases where doubt exists, a sample should be tested before full-scale use.

APPROVALS/ SPECIFICATIONS

DOWSIL 786 Silicone Sealant meets the qualifications of:

- ASTM C 920, Type S, Grade NS, Class 25, Use NT, when tested to glass and aluminum
- FDA Regulation No. 21 CFR 177.2600 (subject to end use compliance with any applicable total extractives limitations)
- NSF ANSI 51 for all food contact types

HOW TO USE

Please consult the Americas Technical Manual, Form No. 62-1112, for detailed information on state-of-the-art application methods and joint design.

Please contact your local Sales Application Engineer for specific advice.

Preparatory Work

Bonding surfaces on both new and remedial jobs must be sound, clean, dry, and free of dust, frost, and soap residue.

Wipe surfaces using clean rag saturated with solvent such as isopropyl alcohol or mineral spirits.

CAUTION: When using flammable solvents, keep away from heat and open flames. Use only with adequate ventilation. Avoid prolonged or repeated skin contact. Always follow solvent container label instructions.

Do not flood surfaces with more solvent than necessary. Do not clean surfaces with soap, detergent or any water-based cleaner. Make sure that apparently clean surfaces are not covered with a thin film of construction dust.

Priming

Although primers are not usually required on ceramic, glass and glazed surfaces, it is possible that certain products should be primed for maximum adhesion. A bead of the silicone sealant on the substrate material to test adhesion prior to general job use is always recommended.

Masking

If bead lines of exact shapes are required, use masking tape before applying DOWSIL 786 Silicone Sealant. Remove immediately after a bead is completed and before a “skin” forms (5–10 minutes).

Application

DOWSIL 786 Silicone Sealant can be applied directly from the caulking cartridge with either an air-operated or hand-operated cartridge gun. Do not break the cartridge seal until just before use.

After applying the sealant and a skin has formed, do not disturb the joint for 48 hours. A previously opened cartridge may be reused by removing the cured plug of sealant from the tip.

Tooling

Tooling is recommended and, if possible, should be completed in one continuous stroke.

Tool the joints within 10 minutes of application. Remove masking tape before a surface skin begins to form. Once a surface skin begins to form, it will be torn off when the tape is removed, leaving a rough surface.

Clean-Up

Excess sealant should be cleaned off tools and surfaces while it is in the uncured state, but using a commercial solvent such as isopropyl alcohol or mineral spirits.

Maintenance

Cured sealant can be cleaned with soap and water. If sealant becomes damaged, replace damaged portion.

HANDLING

PRECAUTIONS

PRODUCT SAFETY

INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

USABLE LIFE AND STORAGE

Product should be stored at or below 32°C (90°F) in original, unopened containers. The shelf life is 810 days

UNRESTRICTED – May be shared with anyone

®™ The DOW Diamond and DOWSIL are trademarks of The Dow Chemical Company

Formica is registered trademark of The Diller Corporation.

DOWSIL™ 786 Silicone Sealant

© 2017 The Dow Chemical Company. All rights reserved.

from date of manufacture. See Use By Date on package.

LIMITATIONS

DOWSIL 786 Silicone Sealant is not recommended for use in applications involving:

- Structural silicone glazing
- Floor joints where physical abuse or abrasion is likely to be encountered
- Prolonged water immersion
- Cementous surfaces, such as masonry
- Building materials that might bleed oils or solvents – materials such as impregnated wood, partially vulcanized rubber gaskets or tapes or adhesives
- Totally confined spaces, because the sealant requires atmospheric moisture for cure
- Surfaces sensitive to corrosion by acetic acid vapors (a byproduct of sealant cure)
- A surface that is intended to be painted

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

SHIPPING LIMITATIONS

None

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

AVAILABILITY

DOWSIL 786 Silicone Sealant is marketed throughout the Americas through construction distributors and building supply outlets.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

www.consumer.dow.com

